

Materialkennwerte Betonstahl in Ringen

	B 500 A	B 500 A (+G)	B 500 A (+P)	B 500 B (WR)	B 500 B Sonderprofil
Streckgrenze ($R_{p0,2}$)	min. 500 N/mm ²	min. 500 N/mm ²	min. 500 N/mm ²	min. 500 N/mm ²	min. 500 N/mm ²
Dehnbarkeit (A_{gt})	min. 3,0 %	min. 3,0 %	min. 3,0 %	min. 5,0 %	min. 5,0 %

	Fero 550 A	Fero 550 B	Fero 550 B (WR)
Streckgrenze ($R_{p0,2}$)	min. 550 N/mm ²	min. 550 N/mm ²	min. 550 N/mm ²
Dehnbarkeit (A_{gt})	min. 2,5 %	min. 5,0%	min. 5,0 %